



AUSTINVILLE LIMESTONE CO. INC.

223 Newtown Church Road Austinville Va 24312

800-289-5963

Product Analysis

Pelletized Dolomitic Limestone

Also sold as: Pelletized LawnLime and Pro Pellets

	Minimum Guaranteed
SCREEN ANALYSIS (before pelletizing)	% Passing
10 mesh	100%
20 mesh	90%
40 mesh	70%
50 mesh	60%
60 mesh	55%
100 mesh	40%
CHEMICAL ANALYSIS	Content by Weight
Calcium (Ca)	20.0%
Magnesium (Mg)	11.5%
Calcium Oxide (CaO)	28.0%
Magnesium Oxide (MgO)	19.1%
Calcium Carbonate (CaCO ₃)	50.0%
Magnesium Carbonate (MgCO ₃)	40.0%
Calcium Carbonate Equivalent (CCE)	97.6%
Effective Neutralizing Power (ENP)	1507 lbs. per ton
Effective Neutralizing Value (ENV)	64.0%
Total Neutralizing Power (TNP)	97.0%
Relative Neutralizing Value (RNV)	88.0%
This product requires 1844 lbs. to equal one ton of standard liming material (with CCE of 90%).	
Agricultural Liming Materials Classification	Medium Ground
CAS# 16389-88-1	
Moisture Content	<1%